

RENO P520 EASY

SOLVENT FREE 2K REPAIR RESIN BASED ON WATER GLASS

KEY BENEFITS

- Very low odour
- Quick and easy processing
- Slight mixing in the container



APPLICATIONS

DESTINATIONS

RENO P520 EASY is a solvent-free 2K repair resin based on water glass for the non-positive sealing of screed cracks and joints. Suitable for gluing e.g. metal profiles and strips.

PRODUCT CHARACTERISTICS

Composition / colour	Water glass based reaction plastic Component A: transparent Component B: brownish
Working time*	10 - 14 minutes at 20° C
Walk on time*	after 15-20 minutes, depending on room temperature and substrate condition
Open time*	Approx. 24 hours
Curing time* / Floor installation	approx. 20 - 30 minutes at 23° C (at 65% rel. LF)
Coverage	Depending on crack width and depth: 1 mixture yields approx. 600 ml

*these times are determined at + 23° C and 50 % relative humidity on normally absorbent substrates

SUBFLOOR PREPARATION

CLEANING PREPARATION

The substrate must be dry, clean (free from layers that would impair adhesion) and load-bearing in accordance with the requirements of DIN 18365 or DIN 18356, DIN 18352 (or standard sheets of the respective area of application).

METHOD OF USE

Cut open the cracks to be closed and place 8 cm long cross sections at 25 cm intervals. Vacuum out incisions with a vacuum cleaner. Pour component B into the bottle containing component A. After closing the bottle, shake component A vigorously for approx. 15 seconds. Insert screed wave connectors into the cross sections at a depth of up to 2/3 of the screed thickness. Pour homogeneously mixed resin from the bottle into the prepared crack and smooth it down with a spatula. Metal profiles and strips must be sanded and degreased. Apply the repair resin to the substrate with a suitable toothed strip and immediately insert/join the parts to be bonded and press on well. In order to improve the adhesive bond of the levelling compounds or adhesives to be applied afterwards, sprinkle the surface of the fresh material with fire-dried Bostik quartz sand (0.1 - 0.5 mm).

OCCUPATIONAL SAFETY AND ENVIRONMENTAL PROTECTION

Please observe the hazard warnings and safety advice on the containers and in the safety data sheets.

COVERAGE

Depending on crack width and depth: 1 mixture yields approx. 600 ml

STORAGE STABILITY

Store in a cool and dry place. Can be stored in its original packaging for approx. 12 months.

CLEANING

Clean tools and fresh spillages with water.

Code	UC	PCB	GENCOD
30616193	0.6 kg	1	4008373130801

SAFETY

For more details, consult the safety data sheet on <https://bostiksd.thevercs.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

