

Cemflow Industrial

Industrial grade floor topping



DESCRIPTION

Cemflow Industrial is a self-smoothing, dimensionally stable, and fast drying industrial grade floor topping for upgrading and renovating new and existing internal floors.

Cemflow Industrial is supplied as a pre-blended dry powder designed for application between 5 mm to 15 mm (in one application) to provide a finished industrial floor. Cemflow Industrial is also available in a different grade (Cemflow Industrial HT) which allows it to be applied at thickness ranging between 5 mm and 30 mm.

Typically Cemflow Industrial can be pumped up to 1500 m² per day. Coverage of 600 m² can be achieved when hand applied, dependent upon manpower and equipment used.

Cemflow Industrial is recommended to be sealed in areas where water may come into direct contact with the cured material. Cemflow Industrial may be sealed with Strongcoat WD water based epoxy coating, or if a matt finish is required Cemflow Sealer can be used. (Further information is available from our Technical Department or the Product Data Sheets).

APPLICATIONS

Cemflow Industrial is suitable for use in a wide range of industrial environments such as warehouses, food processing plants etc. subjected to medium to heavy traffic.

ADVANTAGES

- › Single component, requires only addition of water.
- › Fast setting.
- › Easy and fast application.
- › Excellent adhesion.
- › Excellent abrasion resistance.

STANDARDS

Cemflow Industrial complies with EN 13813, Class CT-C40-F7-AR2.

METHOD OF USE

SUBSTRATE PREPARATION

Concrete and sand/cement screeds must be sound, dry and fully cured (not subject to shrinkage) and any laitance or surface treatments must be removed by mechanical means such as grit blasting.

TECHNICAL PROPERTIES:

Density:	2.10 ± 0.05 g/mL
Working time:	20 - 30 min @ 20°C
Setting time:	120 - 180 min @ 20°C
Foot traffic:	4 hr
Light traffic:	24 hr
Heavy traffic:	3 days
Compressive strength: BS EN 13892-2	> 25 N/mm ² @ 1 day > 35 N/mm ² @ 7 days > 45 N/mm ² @ 28 days
Flexural strength: BS EN 13892-2	> 4 N/mm ² @ 1 day > 7 N/mm ² @ 7 days > 10 N/mm ² @ 28 days
Flow properties using 30 mm Ø x 50 mm flow ring: BS EN 12706	110 - 130 mm
Consumption per mm thickness:	1.7 - 1.75 kg/m ²
Application thickness:	5 - 15 mm (Cemflow Industrial) 5 - 30 mm (Cemflow Industrial HT)

The surface tensile strength of the substrate should be a minimum 1.5 N/mm². For uneven surfaces, apply Cemflow Base/Renovation to a minimum 5 mm to provide a smooth level surface, prior to the application of Cemflow Industrial. (Please refer to relevant product Technical Data Sheets).

The concrete substrate should be below 75% RH alternatively Strongcoat DPM should be applied. The temperature of the floor must be maintained above 10°C throughout the application and drying of the Cemflow Industrial.

Prior to application on to impervious surfaces the area should be thoroughly cleaned and lightly scarified. Any existing surfaces should be well bonded (> 1.5 N/mm²). The perimeter of the room and any columns should be isolated using a compressible strip.

For application over underfloor heating please contact DCP Technical Department for specific advice.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com

Cemflow Industrial

PRIMING

TO CONCRETE AND CEMENT SCREEDS

For application onto sand/cement screeds, concrete and other porous substrates, first seal the prepared surface by applying one coat of Cemflow Primer diluted with 3 parts potable water and allow to dry.

Apply a second coat of primer diluted 3:1 by the same method and allow thoroughly to dry. Depending on the porosity of the substrate a further coat may be required.

To confirm if this is necessary a small application area should be undertaken to ascertain the correct priming requirements. As an alternative, Strongcoat Primer may be used.

PRIMING WITH STRONGCOAT PRIMER

Apply one coat Strongcoat Primer and allow to cure. Apply 2nd coat and whilst still tack fully blind with DCP Aggregate at approximately 3 kg/m² until the surface is covered and no resin spots remain.

The rate of application is approximately 3 kg/m². Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Industrial.

To impervious surfaces:

For application on to impervious surfaces, such as tiles, coatings or onto Strongcoat DPM (please read relevant product technical data sheet).

Apply Strongcoat Primer and whilst it is still tacky fully blind with DCP Coarse Aggregate at approximately 3 kg/m², until the surface is covered and no resin spots remain.

Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Industrial.

MIXING

HAND APPLICATION

Use a power-whisk fitted in a heavy-duty slow speed electric drill. Mix in the proportion of 25 kg of powder to 4.5 - 5.0 litres of potable water.

Pour the water into a suitably sized bucket and gradually add the powder while stirring, until a smooth, lump free consistency is achieved. The material should be mixed for a minimum of 3 minutes. Leave to stand for 2 - 3 minutes and mix briefly for 1 minute before applying.

PUMP APPLICATION

Mix the powder and water according to the method recommended by the pump manufacturers. In the case of pumps having a continuous water feed adjust the rate of water flow until the mix is a smooth fluid, uniform grey liquid with no surface separation, producing a flow of approximately 130 mm using a 35cc flow ring.

APPLICATION

Pour or pump the mixed material onto the prepared surface and allow it to attain a smooth finish. The use of a spiked roller will help eliminate entrapped air and smooth out flow lines. Apply Cemflow Industrial at a thickness of 5 mm to 15 mm and Cemflow Industrial HT at a thickness of 5 mm to 30 mm in one pass only.

For the application of any seal coats, please refer to the relevant Technical Data Sheets.

REMARKS

- » Do not place when the substrate temperature is below 10°C or when the ambient temperature is 10°C and falling.
- » Protect from frost.
- » Do not exceed the maximum recommended water content and only use potable cold water.
- » This product is not recommended for external use or situations where water may come into direct contact with the cured material.
- » This product should not be applied to asphalt or bituminous surfaces.

CLEANING

Wash tools with water immediately after use.

PACKAGING

Cemflow Industrial is available in 25 kg bags.

COVERAGE

A 25 kg pack of Cemflow Industrial will cover approximately 2.75 m² at 5 mm thickness.

YIELD

A 25 kg bag using 4.5 litres of clean water will yield approximately 14.0 litres.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com

STORAGE

Cemflow Industrial has a shelf life of 6 months from date of manufacture if stored at temperatures between 10°C and 30°C in unopened bags and under dry warehouse conditions

Protect from frost.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

CAUTIONS

HEALTH AND SAFETY

For further information refer to the Material Safety Data Sheet.

FIRE

Cemflow Industrial is nonflammable.



Cemflow Industrial

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9
United Kingdom
info.uk@dcp-int.com; info@dcp-int.co.uk
www.dcp-int.com

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence